



Paper Type: Original Article

Principles of Crystal Structures for Bravais Lattice: A Study on Symmetry within Lattice and Diffraction Lines in Crystallography

Imoh Ime Ekanem^{1,*} , Aniekan Essienubong Ikpe¹, Victor Etok Udoh²

¹ Department of Mechanical Engineering, Akwa Ibom State, Polytechnic, Nigeria; imoh.ekanem@akwaibompoly.edu.ng; aniekan.ikpe@akwaibompoly.edu.ng.

² Department of Welding and Fabrication Engineering, Akwa Ibom State, Polytechnic, Nigeria; victoreudoh2018@gmail.com.

Citation:

Received: 1 October 2023

Revised: 14 December 2023

Accepted: 3 February 2024

Ekanem, I. I., Ikpe, A. E., & Udoh, V. E. (2024). Principles of crystal structures for bravais lattice: A study on symmetry within lattice and diffraction lines in crystallography. *Biocompounds*, 1(1), 1-23.

Abstract

Crystallography is a crucial field in materials science and chemistry, as it allows researchers to determine the atomic arrangement within crystalline materials. Understanding the symmetry properties of crystal structures is essential for interpreting diffraction patterns accurately. However, the relationship between Bravais lattice symmetry and diffraction lines is not well-understood. This study aims to address this gap in knowledge by investigating the principles of crystal structures for Bravais lattice and their impact on diffraction patterns. To achieve the research objectives, a comprehensive literature review of existing models and simulations was conducted to gather information on the principles of crystal structures, Bravais lattice symmetry and diffraction patterns. The study focused on analyzing the symmetry properties of different Bravais lattices and their corresponding diffraction lines. The findings revealed that the arrangement of lattice points in a crystal structure determines the symmetry properties of the lattice. Moreover, different Bravais lattices exhibit varying degrees of symmetry, which directly influences the diffraction lines observed in Crystallography experiments. The study found that the symmetry operations within a lattice, such as translations, rotations and reflections, play a crucial role in determining the diffraction pattern. The findings contribute to the advancement of materials science and chemistry by enhancing the knowledge required to understand crystal structures and to interpret corresponding diffraction patterns more accurately. However, further research may be conducted to explore the practical applications of these findings in Crystallography and materials science.

Keywords: Crystal structures, Bravais lattice, Symmetry, Diffraction lines, Crystallography.

1 | Introduction

Crystallography is a branch of science that deals with the study of crystals and their structures. One of the fundamental concepts in Crystallography is the Bravais lattice, which describes the arrangement of atoms in a crystal lattice. The principles of crystal structures for Bravais lattice play a crucial role in understanding the symmetry within a lattice and the diffraction lines in Crystallography as well the arrangement of atoms within

 Corresponding Author: imoh.ekanem@akwaibompoly.edu.ng

 <https://doi.org/10.48313/bic.v1i1.25>



Licensee System Analytics. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0>).

a crystal lattice [1]. The Bravais lattice is a mathematical concept that describes the periodic arrangement of atoms in a crystal lattice or the periodic arrangement of points in space that form the basis of a crystal structure. It is named after Auguste Bravais, a French mathematician who first introduced the concept in the 19th century. The Bravais lattice is characterized by its symmetry and the arrangement of lattice points in three-dimensional space. The principles of crystal structures for Bravais lattice are based on the concept of translational symmetry, which describes the repeating pattern of atoms in a crystal lattice [2]. This symmetry is essential for understanding the diffraction patterns that are observed when a crystal is subjected to X-ray or electron diffraction. The diffraction lines that are observed in Crystallography are a result of the interference of X-rays or electrons with the periodic arrangement of atoms in a crystal lattice. These diffraction lines provide valuable information about the structure of the crystal lattice, including the spacing between atoms and the orientation of the crystal lattice [3].

The characteristics of crystal structures are determined by the arrangement of atoms or ions within the lattice. The repeating unit of a crystal lattice is called a unit cell, which is the smallest repeating unit that can be used to build up the entire crystal structure. The patterns of atoms within the unit cell can vary depending on the type of crystal structure, such as cubic, tetragonal, orthorhombic, hexagonal, or monoclinic. These patterns are defined by the lattice parameters, which describe the size and shape of the unit cell. The behaviour of crystal structures is governed by the symmetry operations that relate equivalent points within the lattice [4].

Symmetry operations include translations, rotations, reflections and inversions, which can be used to generate all the points within the lattice from a set of symmetry elements. The presence of symmetry within a crystal lattice can be described using the concept of space groups, which classify the different ways in which symmetry elements can be combined within a lattice. The functions of crystal structures within Bravais lattices are diverse and include determining the physical and chemical properties of materials, such as their mechanical, thermal, electrical and optical properties. Crystal structures also play a crucial role in understanding the diffraction patterns that are produced when a crystal is exposed to X-rays or electrons. These diffraction patterns can be used to determine the atomic arrangement within a crystal lattice, as well as the symmetry elements that are present [5]. This study centers on the principles of crystal structures for Bravais lattice, reviewing the symmetry within lattices and diffraction lines in Crystallography. Crystallography continues to be a powerful tool for studying the structure and properties of materials. The principles of crystal structures for Bravais lattice are essential for understanding the symmetry within a lattice and the diffraction lines that are observed in Crystallography. By studying the arrangement of atoms in a crystal lattice and the diffraction patterns that are produced, valuable insights into the structure and properties of crystals can be gained.

2 | Historical Evolution and Key Milestones of Bravais Lattice

The origins of the concept of Bravais lattices can be traced back to the work of early civilizations such as the ancient Greeks and Egyptians, who observed the regular geometric patterns exhibited by crystals. These early observations laid the foundation for the later development of the concept by scientists such as Johannes Kepler and Robert Hooke, who further explored the structure and properties of crystalline materials [6]. The study of crystal structures has been a fundamental aspect of materials science and solid-state physics for centuries. The concept of crystal structures dates back to the early 19th century when scientists began to investigate the regular arrangement of atoms within crystalline materials. Historical records show that the concept of Bravais lattices was first introduced by Auguste Bravais in 1850 [7]. Bravais was a French mathematician and physicist who developed a mathematical framework for describing the symmetry of crystal structures and the arrangement of atoms in a crystal lattice.

The development laid the foundation for the study of Crystallography and provided a systematic way to classify different types of crystal structures based on their symmetry. The development was further expanded upon by scientists such as William Lawrence Bragg and Max von Laue, who developed the mathematical tools necessary to analyze the diffraction patterns produced by crystals. The historical evolution of crystal structures

for Bravais lattices has been marked by a series of important discoveries and breakthroughs. For example, in the early 20th century, scientists such as Max von Laue and William Henry Bragg made significant contributions to the field of Crystallography by developing the theory of X-ray diffraction. This theory provided a powerful tool for studying the structure of crystals and laid the foundation for modern Crystallography. Some of the simplest and most common types of Bravais lattices are:

- I. The primitive cubic lattice: these consists of atoms arranged in a simple cubic structure with one atom at each lattice point. This lattice was first described by Auguste Bravais in 1850 and has since been extensively studied and used as a model for understanding the properties of crystalline materials [8].
- II. The body-centered cubic lattice: these has an additional atom at the center of each cube. This lattice was first described by Charles-Victor Mauguin in 1912 and has been used to study a wide range of materials, including metals and alloys.
- III. The face-centered cubic lattice: this is another common type of Bravais lattice, in which there is an additional atom at the center of each face of the cube. This lattice was first described by Auguste Bravais in 1850 and has been used to study a variety of materials, including semiconductors and insulators [9].

The concept of Bravais lattices has continued to evolve in the modern era, with advancements in Crystallography and materials science leading to a deeper understanding of the structure and properties of crystalline materials. Today, the concept of Bravais lattices plays a crucial role in fields such as solid-state physics, materials science and chemistry, where it is used to describe the arrangement of atoms in a wide range of materials. The key milestones in the development of Bravais lattices are:

- I. The discovery of the seven crystal systems by René Just Haüy in the late 18th century. Haüy identified seven distinct ways in which atoms could be arranged in a crystal lattice, based on their symmetry and unit cell shape. These crystal systems laid the foundation for the classification of crystal structures and provided a framework for understanding the relationship between the structure of a material and its properties [10].
- II. Another important milestone in the study of Bravais lattices was the development of the concept of space groups by Arthur Schoenflies and William Barlow in the early 20th century. Space groups are mathematical descriptions of the symmetry operations that can be applied to a crystal lattice and they provide a systematic way to classify and analyze crystal structures. The identification of space groups allowed researchers to predict the possible arrangements of atoms in a crystal lattice and to study the effects of symmetry on the properties of materials [11].

The Bravais lattice is a fundamental concept in materials science that describes the arrangement of atoms or ions in a crystal structure. It provides a mathematical framework for understanding the periodicity and symmetry of crystalline materials. The Bravais lattice is named after Auguste Bravais, a French physicist who made significant contributions to the study of Crystallography in the 19th century. It is a mathematical representation of the repeating pattern of atoms or ions in a crystal lattice. The lattice points, which represent the positions of the atoms or ions, are arranged in a periodic manner, forming a three-dimensional network.

3 | Recent Trends and Industrial Advancement in the Field of Bravais Lattices

The study of crystal structures has been a fundamental aspect of materials research for centuries, with the development of the Bravais lattice providing a framework for understanding the arrangement of atoms in a crystal. It provides a systematic way to classify different types of crystal structures based on their symmetry and unit cell dimensions. The Bravais lattice is characterized by three basis vectors, known as a , b and c , which define the periodicity of the crystal structure [12], [13]. In recent years, there have been significant advancements in the study of crystal structures, leading to a deeper understanding of their properties and potential applications. Recent industrial advancements in this field have led to significant progress in the development of new materials with tailored properties for a wide range of applications. Some of the conventional trends in the study of crystal structures highlighted as follows:

- I. The use of X-ray diffraction techniques to determine the atomic arrangement in a crystal: X-ray diffraction is a powerful tool that allows researchers to analyze the crystal structure of a material by measuring the diffraction pattern produced when X-rays interact with the atoms in the crystal lattice. This technique has been widely used in materials science to study the structure of various materials, including metals, ceramics and semiconductors [14].
- II. In recent years, there have been significant advancements in the study of crystal structures, driven by advances in computational modeling and experimental techniques. Computational methods, such as Density Functional Theory (DFT) and molecular dynamics simulations, have enabled researchers to predict the crystal structure of a material with high accuracy and efficiency. These methods have been used to study the properties of complex materials, such as alloys and nanoparticles and to design new materials with tailored properties for specific applications.
- III. The development of new experimental techniques, such as electron microscopy and synchrotron radiation, which allow researchers to visualize the atomic structure of materials with unprecedented resolution. These techniques have provided new insights into the behaviour of materials at the atomic level and have opened up new possibilities for the design of advanced materials with novel properties [15].
- IV. The development of advanced manufacturing techniques for producing complex crystal structures with high precision: for example, additive manufacturing technologies such as 3D printing can be used to fabricate intricate lattice patterns with sub-micron resolution, enabling the creation of materials with tailored mechanical, thermal and optical properties. These advancements have the potential to revolutionize industries such as aerospace, automotive and healthcare by enabling the production of lightweight, high-performance components with unprecedented levels of customization [16].
- V. The use of advanced computational techniques to design and optimize novel crystal structures: by leveraging the power of high-performance computing, researchers are able to explore a vast space of possible lattice configurations and identify those with desirable properties, such as high strength, flexibility, or conductivity. This approach has led to the discovery of new materials with unprecedented performance characteristics, opening up new possibilities for applications in areas such as electronics, energy storage and catalysis.

Recent industrial advancements in the field of Bravais lattices have opened up new opportunities for the design and fabrication of advanced materials with tailored properties for a wide range of applications. By leveraging advanced computational techniques and manufacturing technologies, researchers are able to explore new frontiers in materials science and engineering, leading to the development of innovative solutions to complex technological challenges. As these advancements continue to evolve, we can expect to see further breakthroughs in the design and synthesis of novel materials with unprecedented performance characteristics, driving progress in industries ranging from electronics to healthcare.

4 | Types of Bravais Lattices

There are several types of Bravais lattices, which are classified based on their symmetry properties. Each type of Bravais lattice has its own unique symmetry properties, which determine the overall structure of the crystal lattice. Bravais lattices are a set of 14 unique lattice structures that describe the arrangement of atoms in a crystal. These lattices play a crucial role in the study of Crystallography and solid-state physics, as they provide a framework for understanding the properties of crystalline materials [17]. The different types of Bravais lattices are as follows:

- I. Cubic system: the cubic system is the simplest and most symmetrical crystal system which consists of atoms arranged in a cubic structure with one atom at each lattice point. The cubic system can be calculated using Eq. (1).

$$\frac{1}{d^2} = \frac{h^2 + k^2 + l^2}{a^2}. \quad (1)$$

This lattice is characterized by a lattice constant, which is the distance between adjacent lattice points [18].




Fig. 1. Cubic system bravais lattices [19].

- II. Body-centered cubic lattice: this is similar to the simple cubic lattice but with an additional atom at the center of the unit cell. This lattice has a higher packing density than the simple cubic lattice.
- III. Face-centered cubic lattice: these has atoms at the corners and the center of each face of the unit cell. This lattice is commonly found in metals such as copper and aluminum.
- IV. Tetragonal system: in the tetragonal system, the lattice points form a rectangular prism with different lengths along the three axes. The atoms arranged in a rectangular structure with two lattice vectors of equal length and one lattice vector of a different length. The tetragonal system can be calculated using Eq. (2).

$$\sin^2\theta = A(h^2 + k^2) + Cl^2, \quad (2)$$

where $A (= \lambda^2/4a^2)$ and $C (= \lambda^2/4c^2)$ are constants for any pattern. This lattice is commonly found in materials such as zirconium [20].

- V. Orthorhombic system: in the orthorhombic system, the lattice points form a rectangular prism with unequal lengths along the three axes. The orthorhombic system can be calculated using Eq. (3).

$$\frac{1}{d^2} = \frac{h^2}{a^2} + \frac{k^2}{b^2} + \frac{l^2}{c^2}. \quad (3)$$

This lattice is commonly found in materials such as sulfur.

- VI. Rhombohedral system: the rhombohedral system has a rhombohedral unit cell, which is a distorted cube with angles that are not right angles. The rhombohedral system can be calculated using Eq. (4).

$$\frac{1}{d^2} + \frac{(h^2 + k^2 + l^2)\sin^2\alpha + hk + kl + hl)\cos^2\alpha - \cos\alpha}{a^2(1 - 3\cos^2\alpha + 2\cos^3\alpha)}. \quad (4)$$

This lattice is commonly found in materials such as calcite [21].

- VII. Hexagonal system: these consists of atoms arranged in a hexagonal structure with one atom at each lattice point. This lattice is commonly found in materials such as graphite and some metals. The hexagonal system has a hexagonal unit cell, which is a prism with a hexagonal base and equal lengths along the three axes.
- VIII. Monoclinic system: the monoclinic system has a parallelepiped unit cell with unequal lengths along the three axes and one angle that is not a right angle. It has atoms arranged in a rectangular structure with one lattice vector at a different angle than the other two.

This lattice is commonly found in materials such as gypsum [22].






Crystal Family	Point Group	5 Bravais Lattices	
		Primitive	Centred
Monoclinic	C_2	 Oblique	
Orthorhombic	D_2	 Rectangular	 Centred Rectangular
Tetragonal	D_4	 Square	
Hexagonal	D_6	 Hexagonal	

Fig. 2. 2-D representation of various Bravais lattices [23].

- IX. Triclinic system: the triclinic system has a parallel piped unit cell with unequal lengths along the three axes and all angles that are not right angles. The atoms are arranged in a parallelogram structure with all three lattice vectors at different angles to each other. The triclinic system can be calculated using Eq. (5).

$$abc\sqrt{1 - \cos^2\alpha - \cos^2\beta - \cos^2\gamma + 2\cos\alpha \cos\beta \cos\gamma}. \quad (5)$$

This lattice is commonly found in materials such as plagioclase feldspar [24].

- X. Primitive rectangular lattice: these has atoms arranged in a rectangular structure with one lattice vector longer than the other two. This lattice is commonly found in materials such as lead.
- XI. Centered rectangular lattice: this is similar to the primitive rectangular lattice but with an additional atom at the center of the unit cell. This lattice is commonly found in materials such as iron [25].
- XII. Primitive hexagonal lattice: this system has atoms arranged in a hexagonal structure with one lattice vector longer than the other two. This lattice is commonly found in materials such as beryllium.
- XIII. Centered hexagonal lattice: this is similar to the primitive hexagonal lattice but with an additional atom at the center of the unit cell. This lattice is commonly found in materials such as cobalt.
- XIV. Cubic lattice: these has atoms arranged in a cubic structure with all three lattice vectors of equal length. This lattice is commonly found in materials such as sodium chloride [26].

The 14 different types of Bravais lattices provide a comprehensive framework for understanding the arrangement of atoms in crystalline materials. It allows scientists to predict and explain various properties of materials, such as their mechanical, electrical and optical behaviour. In addition, the Bravais lattice is a fundamental concept in materials science that describes the arrangement of atoms or ions in a crystal lattice. It provides a mathematical framework for understanding the periodicity and symmetry of crystalline materials.

5 | Types of Crystal Structures for Bravais Lattice

Crystal structures play a crucial role in understanding the properties and behaviour of materials. The Bravais lattice is a fundamental concept in Crystallography that describes the arrangement of lattice points in a crystal. There a few distinct types of Bravais lattices, each characterized by its unique symmetry and arrangement of lattice points. The different types of Bravais Lattices are stated as follows:

- I. Simple cubic (P) Bravais lattice: the simple cubic lattice is the most basic and straightforward Bravais lattice. It consists of lattice points positioned at the corners of a cube, with each lattice point representing an atom or ion. Sodium chloride (NaCl) crystal structure is a classic example of a simple cubic lattice. In NaCl, sodium ions occupy the lattice points, while chloride ions occupy the octahedral voids between them. This crystal structure is widely used in the study of ionic compounds and their properties [27].
- II. Body-centered cubic (I) Bravais lattice: the body-centered cubic lattice is characterized by an additional lattice point at the center of the cube, in addition to the corner points. Iron (Fe) crystal structure is a prominent example of a body-centered cubic lattice. In this structure, iron atoms occupy both the corner and body-centered positions, resulting in a more densely packed arrangement. The body-centered cubic lattice is commonly found in metals and alloys and its understanding is crucial in understanding their mechanical and thermal properties [28].




Fig. 3. Body-centered cubic (I) Bravais lattice [29].

- III. Face-centered cubic (F) Bravais lattice: the face-centered cubic lattice is characterized by lattice points at the corners and centers of each face of the cube. Copper (Cu) crystal structure is a well-known example of a face-centered cubic lattice. In Cu, copper atoms occupy both the corner and face-centered positions, resulting in a highly symmetric and closely packed structure. This lattice type is commonly found in metallic elements and is essential in understanding their electrical and thermal conductivity.
- IV. Hexagonal (P) Bravais lattice: the hexagonal lattice is unique among the Bravais lattices due to its non-cubic symmetry. Graphite crystal structure is a notable example of a hexagonal lattice. In graphite, carbon atoms are arranged in a hexagonal lattice, forming layers that are stacked on top of each other. This structure gives graphite its unique properties, such as its lubricating nature and electrical conductivity perpendicular to the layers. Understanding the hexagonal lattice is crucial in studying layered materials and their applications.

Crystal structures for different Bravais lattices provide a foundation for understanding the properties and behaviour of various materials. The examples discussed in this section, including simple cubic, body-centered cubic, face-centered cubic and hexagonal lattices, represent a diverse range of crystal structures found in different materials. By studying these crystal structures, scientists and engineers can gain insights into the physical, chemical and electrical properties of materials, leading to advancements in various fields such as materials science, chemistry and engineering.

6 | Types of Symmetry within a Lattice

Symmetry is a fundamental concept in mathematics and science, playing a crucial role in understanding the properties and behaviour of various systems. Within the context of lattices, symmetry manifests in different forms, each with its unique characteristics and implications. Types of symmetry found within a lattice are stated as follows:

- I. Translational symmetry: translational symmetry is the most basic form of symmetry observed in a lattice. It refers to the repeated pattern of identical units that are shifted by a constant vector, known as the lattice translation vector. This type of symmetry is essential in defining the periodicity and regularity of the lattice structure. It allows for the prediction of lattice properties, such as the arrangement of atoms or molecules and facilitates the understanding of crystallographic structures.




Fig. 4. Translational symmetry [30].

- II. Rotational symmetry: rotational symmetry refers to the ability of a lattice to exhibit identical patterns upon rotation about a specific axis. In a lattice, rotational symmetry can be observed when the arrangement of atoms or molecules remains unchanged after a certain angle of rotation. The order of rotational symmetry is determined by the number of times the pattern repeats within a full rotation. For example, a lattice with a three-fold rotational symmetry will exhibit the same pattern every 120 degrees.
- III. Reflectional symmetry: reflectional symmetry, also known as mirror symmetry, occurs when a lattice exhibits an identical pattern on either side of a mirror plane. This type of symmetry is characterized by the reflection of the lattice structure across the plane, resulting in a mirror image. Reflectional symmetry is often observed in crystals and is crucial in determining their optical properties, such as birefringence [31].
- IV. Inversion symmetry: inversion symmetry, also referred to as center of symmetry, occurs when a lattice exhibits an identical pattern when inverted through a central point. This type of symmetry is observed when the arrangement of atoms or molecules remains unchanged after being inverted. Inversion symmetry is particularly important in the study of chiral molecules and crystals, as it determines their optical activity and enantiomeric properties [32].

The types of symmetry within a lattice, including translational, rotational, reflectional and inversion symmetry, plays a crucial role in understanding the properties and behaviour of various systems. These symmetries allow for the prediction of lattice properties, facilitate the study of crystallographic structures and determine optical properties.

7 | Lattice Directions in Reference to Vector Relationships and Lattice Vectors

Lattice directions play a crucial role in the arrangement of atoms or ions in a crystal lattice. These directions are defined by vector relationships and lattice vectors, which provide a framework for describing the spatial arrangement of lattice points. This section discusses the concept of lattice directions, its relationship with and lattice vectors and significance in Crystallography.

- I. Lattice vectors: lattice vectors are fundamental vectors that define the unit cell of a crystal lattice. They represent the translation required to move from one lattice point to another within the crystal structure. Lattice vectors are typically denoted as a , b and c and their linear combinations determine the position of any lattice point within the crystal lattice [33].
- II. Vector relationships: vector relationships are essential in understanding the orientation and arrangement of lattice points within a crystal lattice. These relationships are established by considering the relative positions of lattice points and the vectors connecting them. By analyzing these vectors, we can determine the direction and magnitude of the lattice vectors.

III. Lattice directions: lattice directions are defined by the relative positions of lattice points and are expressed using Miller indices. Miller indices are a set of three integers (h, k, l) that represent the intercepts of a plane on the crystallographic axes. These indices provide a concise way to describe the orientation and direction of a specific lattice plane within the crystal lattice [34].

The relationship between lattice directions and vector relationships can be understood by considering the vector connecting two lattice points. This vector represents the direction and magnitude of the lattice vector associated with the given lattice direction. By analyzing the vector relationships between lattice points, we can determine the lattice direction and its corresponding Miller indices.

8 | Mathematical Relation of Crystallography

In real space, applying the expressions of the vectors $r = ua_1 + va_2 + wa_3$ and $r^* = r = u^*a_1 + v^*a_2 + w^*a_3$, the angle between two crystallographic directions $[u \ v \ w]$ and $[u^* \ v^* \ w^*]$ within a particular crystal is given by Eq. (6).

$$\begin{aligned} \cos\varphi &= \frac{r \cdot r^*}{|r| \cdot |r^*|} \\ &= \frac{(ua_1 + va_2 + wa_3)(u^*a_1 + v^*a_2 + w^*a_3)}{\sqrt{(ua_1 + va_2 + wa_3)(ua_1 + va_2 + wa_3)} \sqrt{(u^*a_1 + v^*a_2 + w^*a_3)(u^*a_1 + v^*a_2 + w^*a_3)}} \end{aligned} \quad (6)$$

When two vectors are mutually perpendicular to each other, the relationship is given by Eq. (7).

$$(ua_1 + va_2 + wa_3)(u^*a_1 + v^*a_2 + w^*a_3) = 0. \quad (7)$$

In events where all the angles between translation vectors are 90°, Eq. (6) translates into Eq. (8).

$$\cos\varphi = \frac{uu^*a^2 + vv^*b^2 + ww^*c^2}{\sqrt{(ua)^2 + (vb)^2 + (wc)^2} \sqrt{(u^*a)^2 + (v^*b)^2 + (w^*c)^2}} \quad (8)$$

where $|a_1| = a$, $|a_2| = b$, $|a_3| = c$.

When two crystallographic directions are mutually perpendicular to each other, the relationship is given by Eq. (9).

$$uu^*a^2 + vv^*b^2 + ww^*c^2 = 0. \quad (9)$$

The bond length denoted as L is derived between two atoms occupying positions x_1, y_1, z_1 and x_2, y_2, z_2 within a particular crystal, and is expressed by the relationship in Eq. (10).

$$\begin{aligned} L &= \sqrt{[(x_2 - x_1)a_1 + (y_2 - y_1)a_2 + (z_2 - z_1)a_3][(x_2 - x_1)a_1 + (y_2 - y_1)a_2 + (z_2 - z_1)a_3]}. \end{aligned} \quad (10)$$

In events where all the angles between translation vectors are 90°, Eq. (10) translates into Eq. (11).

$$L = \sqrt{(x_2 - x_1)^2 a^2 + (y_2 - y_1)^2 b^2 + (z_2 - z_1)^2 c^2}, \quad (11)$$

where $|a_1| = a$, $|a_2| = b$, $|a_3| = c$.

On the other hand reciprocal space relates more to crystallographic planes. Computing the angle between crystallographic planes $[h \ k \ l]$ and $[h^* \ k^* \ l^*]$ within the same structure: $H = hb_1 + kb_2 + lb_3$ and $H^* = h^*b_1 + k^*b_2 + l^*b_3$, we find:

$$\begin{aligned} \cos\varphi &= \frac{H \cdot H^*}{|H| \cdot |H^*|} \\ &= \frac{(hb_1 + kb_2 + lb_3)(h^*b_1 + k^*b_2 + l^*b_3)}{\sqrt{(hb_1 + kb_2 + lb_3)(hb_1 + kb_2 + lb_3)} \sqrt{(h^*b_1 + k^*b_2 + l^*b_3)(h^*b_1 + k^*b_2 + l^*b_3)}} \end{aligned} \quad (12)$$

When two planes are mutually perpendicular to each other, the relationship is given by Eq. (13).

$$(hb_1 + kb_2 + lb_3)(h^*b_1 + k^*b_2 + l^*b_3). \quad (13)$$

In events where all the angles between vectors in reciprocal space are 90°, Eq. (12) can be simplified into Eq. (14).

$$\cos\varphi = \frac{\left(\frac{hh^*}{a^2}\right) + \left(\frac{kk^*}{b^2}\right) + \left(\frac{ll^*}{c^2}\right)}{\sqrt{\left(\frac{h}{a}\right)^2 + \left(\frac{k}{b}\right)^2 + \left(\frac{l}{c}\right)^2} \sqrt{\left(\frac{h^*}{a}\right)^2 + \left(\frac{k^*}{b}\right)^2 + \left(\frac{l^*}{c}\right)^2}}. \quad (14)$$

When two crystallographic planes are perpendicular to each other, the relationship is given by Eq. (15).

$$\left(\frac{hh^*}{a^2}\right) + \left(\frac{kk^*}{b^2}\right) + \left(\frac{ll^*}{c^2}\right) = 0. \quad (15)$$

The orthogonality condition for crystallographic planes can be expressed in its simplest form in cubic crystals [$a = b = c$] is given by Eq. (16).

$$hh^* + kk^* + ll^* = 0. \quad (16)$$

In reciprocal space, the length of vector H, which relates to d-spacing between planes [h k l] is given by Eq. (17).

$$|H| = \frac{1}{d} = \sqrt{(hb_1 + kb_2 + lb_3)(hb_1 + kb_2 + lb_3)}. \quad (17)$$

Applying Eq. (17) to cubic crystal yields:

$$d^{-1} = \sqrt{\frac{h^2 + k^2 + l^2}{a^2}}. \quad (18)$$

Applying Eq. (17) to tetragonal crystal yields:

$$d^{-1} = \sqrt{\frac{h^2 + k^2}{a^2} + \frac{l^2}{c^2}}. \quad (19)$$

Applying Eq. (17) to hexagonal crystal yields:

$$d^{-1} = \sqrt{\frac{4}{3} \frac{h^2 + hk^2 + k^2}{a^2} + \frac{l^2}{c^2}}. \quad (20)$$

In events where the computation of an angle between crystallographic direction $r[u \ v \ w]$ and plane $H[h \ k \ l]$ is required, the Equation is given by Eq. (21).

$$\begin{aligned} \cos\varphi &= \frac{r \cdot H}{|r| \cdot |H|} = \frac{(ua_1 + va_2 + wa_3)(hb_1 + kb_2 + lb_3)}{|r| \cdot |H|} \\ &= \frac{uh + vk + wl}{\sqrt{(ua_1 + va_2 + wa_3)(ua_1 + va_2 + wa_3)} \sqrt{(hb_1 + kb_2 + lb_3)(hb_1 + kb_2 + lb_3)}}. \end{aligned} \quad (21)$$

All the vectors with identical indices in cubic crystals are parallel, as there are no distinctions between real and reciprocal space [35]. Substituting $u = h$, $v = k$, $w = l$ in Eq. (21), alongside with $|a_1| = a$, $|b_1| = \frac{1}{a}$, $\alpha = \beta = \gamma = 90^\circ$, yields:

$$\cos\varphi = \frac{h^2 + k^2 + l^2}{a\sqrt{h^2 + k^2 + l^2} * \left(\frac{1}{a}\right)\sqrt{h^2 + k^2 + l^2}} = 1 \text{ and } \varphi = 0. \quad (22)$$

However, any given reduction in the symmetry may result in a finite angle between the vectors $r[u\ v\ w]$ and plane $H[h\ k\ l]$ which are no longer parallel. For instance in tetragonal crystals $|a_1| = |a_2| = a, |a_3| = c, |b_1| = |b_2| = \frac{1}{a}, |b_3| = \frac{1}{c}$ and $\alpha = \beta = \gamma = 90^\circ$, this angle equals:

$$\cos\varphi = \frac{h^2 + k^2 + l^2}{\sqrt{h^2 + k^2 + \left(\frac{c}{a}\right)^2 l^2} * \sqrt{h^2 + k^2 + \left(\frac{c}{a}\right)^2 l^2}}. \quad (23)$$

It can be clearly seen again that the vectors r and H are sensitive to the tetragonal form of the unit cell, therefore, constitute both projections h, k and l which are non-parallel [$\varphi \neq 0$].

9 | Lattice Directions in Relation to Angles between Directions in Cubic Crystals

In the field of Crystallography, the relationship between lattice directions and the angles between them is crucial for characterizing the structure and properties of cubic crystals. Lattice directions are defined by the crystallographic axes, which are imaginary lines that intersect at the origin of the crystal lattice. The significance of lattice directions and their angles in cubic crystals are highlighted as follows:

- I. Lattice directions in cubic crystals: cubic crystals possess a high degree of symmetry, making them ideal for studying the relationship between lattice directions and angles. The crystallographic axes in cubic crystals are mutually perpendicular, forming a right-handed coordinate system. These axes are labeled as a, b and c , with a corresponding set of lattice directions $[100], [010]$ and $[001]$, respectively [36].




Fig. 5. Lattice directions in cubic crystals [37].

- II. Angles between lattice directions: the angles between lattice directions in cubic crystals are of great interest in Crystallography. The angles between the $[100], [010]$ and $[001]$ directions are all 90 degrees, reflecting the cubic symmetry. This symmetry is a result of the equal spacing between lattice planes in all directions, leading to the formation of a regular, three-dimensional lattice structure [38].
- III. Its importance in Crystallographic studies: the knowledge of lattice directions and their angles is essential for crystallographers to determine crystal symmetry, identify crystal faces and understand crystal growth patterns. By analyzing the angles between lattice directions, crystallographers can classify crystals into different crystal systems, such as cubic, tetragonal, orthorhombic, etc. This classification aids in predicting crystal properties, including mechanical, electrical and optical behavior [39].
- IV. Lattice directions and their angles play a crucial role in crystallographic calculations. For instance, when determining the Miller indices of crystallographic planes, the angles between lattice directions are used to normalize the indices and define the orientation of the planes within the crystal lattice. This information is vital for interpreting X-ray diffraction patterns, which provide valuable insights into the crystal structure.

Lattice directions and their angles are fundamental concepts in Crystallography, particularly in the study of cubic crystals. The cubic symmetry of these crystals allows for a straightforward relationship between lattice directions and angles, with all angles being 90 degrees. Understanding these relationships is essential for characterizing crystal structures, predicting crystal properties and interpreting experimental data. Crystallographers rely on this knowledge to advance our understanding of materials and their applications in various fields, including materials science, solid-state physics and chemistry.

10 | Lattice Directions in Relation to Vector Relationships

Lattice directions play a crucial role in understanding the relationship between vectors in crystal structures. A lattice direction refers to a specific direction within a crystal lattice, which can be described using Miller indices. These indices provide a convenient way to express the orientation and magnitude of a vector within a crystal lattice [40]. By understanding lattice directions, researchers can gain insights into the physical properties and behaviour of materials. The significance of lattice directions in relation to vector relationships within crystal structures are stated as follows:

- I. Lattice directions and Miller indices: Miller indices are a set of three integers that represent the orientation of a plane or a direction within a crystal lattice. These indices are denoted as (hkl) , where h , k and l are the reciprocals of the intercepts made by the plane or direction with the crystallographic axes. For example, a lattice direction represented as (uvw) corresponds to the direction that intersects the crystallographic axes at u , v and w units, respectively [12].
- II. Vector relationships and lattice directions: lattice directions are closely related to vector relationships within crystal structures. A vector can be defined as a quantity that has both magnitude and direction. In Crystallography, vectors are used to describe various physical properties, such as atomic displacements, lattice vibrations and crystal growth. By understanding the lattice directions associated with these vectors, researchers can gain insights into the underlying crystal structure and its properties.
- III. Lattice translation: lattice translation refers to the movement of a lattice point along a specific lattice direction. This movement can be described using vector addition and subtraction. For example, if we have two vectors A and B , their sum $(A + B)$ represents the lattice translation along the direction defined by the sum of their respective lattice directions. Similarly, the difference $(A - B)$ represents the lattice translation along the direction defined by the difference of their lattice directions [41].
- IV. Lattice directions: lattice directions also play a crucial role in understanding crystal symmetry. Crystal symmetry refers to the repeating patterns and arrangements of atoms within a crystal lattice. By analyzing the lattice directions associated with different crystal planes and directions, researchers can determine the symmetry elements present in a crystal structure. These symmetry elements include rotations, reflections and translations, which are essential for understanding the physical properties and behaviour of materials [42].

Lattice directions are fundamental in understanding the relationship between vectors within crystal structures. Miller indices provide a convenient way to express the orientation and magnitude of a vector within a crystal lattice. By analyzing lattice directions, researchers can gain insights into vector relationships, lattice translations and crystal symmetry. This knowledge is crucial for understanding the physical properties and behaviour of materials, which has significant implications in various scientific and technological fields. Further research in this area will continue to enhance our understanding of crystal structures and their applications.

11 | Lattice Directions in Relation to Lattice Vectors

In the field of Crystallography, lattice directions play a crucial role in understanding the arrangement of atoms within a crystal lattice. These directions are closely related to lattice vectors, which define the periodicity and symmetry of the crystal lattice. The concept of lattice directions in relation to lattice vectors are:

- I. Lattice vectors: lattice vectors are fundamental vectors that define the unit cell of a crystal lattice. They represent the translation symmetry of the lattice and are used to describe the arrangement of atoms within the crystal structure. Lattice vectors are typically denoted as a , b and c and are expressed in terms of their

magnitudes and directions. These vectors are chosen in such a way that they form a parallelepiped, enclosing the unit cell of the crystal lattice [43].

- II. Lattice directions: lattice directions, on the other hand, are vectors that describe the orientation of a specific direction within the crystal lattice. They are represented by square brackets enclosing three integers, known as Miller indices. Miller indices are used to define the direction of a lattice vector with respect to the lattice vectors a , b and c . The Miller indices are determined by taking the reciprocals of the intercepts made by the direction on the respective lattice vectors [44].
- III. Relationship between lattice directions and lattice vectors: lattice directions are closely related to lattice vectors, as they are derived from the lattice vectors themselves. The Miller indices of a lattice direction are directly related to the reciprocals of the intercepts made by the direction on the lattice vectors a , b and c . This relationship allows crystallographers to determine the orientation of specific directions within a crystal lattice using lattice vectors.
- IV. Significance in Crystallography: the concept of lattice directions and lattice vectors is of utmost importance in Crystallography. By understanding the lattice directions, crystallographers can determine the symmetry and periodicity of a crystal lattice. This knowledge is crucial in predicting the physical and chemical properties of materials, as the arrangement of atoms within a crystal lattice directly influences its behaviour [45].

Lattice directions and lattice vectors are fundamental concepts in Crystallography. Lattice vectors define the unit cell and translation symmetry of a crystal lattice, while lattice directions describe the orientation of specific directions within the lattice. The relationship between these two concepts allows crystallographers to determine the arrangement of atoms within a crystal lattice, enabling a deeper understanding of the properties and behaviour of materials.

12 | Lattice Directions in Relation to the Family of Directions

In the field of Crystallography, lattice directions play a crucial role in understanding the arrangement and properties of crystalline materials. Lattice directions are defined as vectors that describe the orientation of a crystal lattice with respect to a reference frame. These directions are essential for characterizing crystallographic planes, determining crystallographic symmetry and analyzing crystal growth patterns. The importance in Crystallography are:

- I. The family of directions: the family of directions refers to a set of crystallographic directions that share similar characteristics and properties. These directions are defined by their Miller indices, which represent the reciprocals of the intercepts made by the direction on the crystallographic axes. The family of directions is denoted by square brackets, such as (uvw) , where u , v and w are integers representing the Miller indices. Each set of Miller indices corresponds to a unique direction within the crystal lattice [46].
- II. Lattice directions: lattice directions are vectors that describe the orientation of a crystal lattice. They are represented by three integers, h , k and l , known as the Miller indices of the direction. These indices are derived from the intercepts made by the direction on the crystallographic axes, similar to the Miller indices of crystallographic planes. Lattice directions are denoted by angle brackets, such as $\langle hkl \rangle$. Each set of Miller indices represents a unique lattice direction [47].
- III. Relationship between lattice directions and the family of directions: lattice directions and the family of directions are closely related in Crystallography. Each lattice direction belongs to a specific family of directions and vice versa. The relationship between the two can be understood by considering the crystallographic symmetry of the lattice. Crystallographic symmetry refers to the repeating patterns of atoms within a crystal lattice. It is characterized by a set of symmetry operations, such as rotations, reflections and translations, which leave the crystal lattice unchanged. The symmetry operations of a crystal lattice can be used to generate equivalent lattice directions. For example, if a lattice direction $\langle hkl \rangle$ belongs to a specific family of directions (uvw) , then all directions obtained by applying symmetry operations to $\langle hkl \rangle$ will also

belong to the same family (uvw). This relationship allows researchers to determine the symmetry of a crystal lattice by analyzing the family of directions associated with a given lattice direction [48].

- IV. Applications in Crystallography research: the understanding of lattice directions and their relationship with the family of directions is crucial in various areas of Crystallography research. For instance, in crystal growth studies, lattice directions help predict the growth patterns of crystals and control their morphology. By manipulating the growth conditions, researchers can influence the orientation of crystal faces and obtain crystals with desired properties [49].

Lattice directions are essential in the analysis of crystallographic defects, such as dislocations and stacking faults. These defects can significantly affect the mechanical, electrical and optical properties of crystalline materials. By characterizing the lattice directions associated with these defects, researchers can gain insights into their formation mechanisms and devise strategies to mitigate their impact. Lattice directions are fundamental vectors that describe the orientation of a crystal lattice. They are closely related to the family of directions, which represents sets of crystallographic directions with similar properties. Understanding the relationship between lattice directions and the family of directions is crucial in Crystallography research, enabling the prediction of crystal growth patterns, analysis of crystallographic defects and determination of crystallographic symmetry.

13 | Miller-Bravais Indices

Miller-Bravais indices are a crucial tool in Crystallography for describing the orientation and intersection of planes within hexagonal crystals. These indices are particularly useful in the case of hexagonal crystals, where the lattice structure exhibits unique characteristics and also provide a systematic and concise way to represent the crystallographic planes and directions, allowing for a better understanding of the crystal structure and its properties. This section will analyze the merits of Miller-Bravais indices in relation to the intersection of planes in hexagonal crystals. And they are:

- I. Hexagonal crystals possess a unique crystal structure characterized by a six-fold rotational symmetry axis. This symmetry results in the presence of three non-equivalent crystallographic axes, two of which are perpendicular to each other and lie in the basal plane, while the third axis is perpendicular to the basal plane. The Miller-Bravais indices are used to describe the orientation and intersection of planes within this crystal structure [50].
- II. In hexagonal crystals, the indices are denoted as (hkil), where h, k, i and l are integers. The (hkil) indices represent a plane that intersects the crystal lattice at the points (h, k, i) and is parallel to the (l) direction. These indices are determined by considering the intercepts of the plane with the crystallographic axes.
- III. The (hkil) indices can be used to describe various planes within a hexagonal crystal lattice. For instance, the (1000) plane represents a plane that intersects the crystal lattice at the points (1, 0, 0) and is parallel to the c-axis. Similarly, the (1010) plane intersects the lattice at (1, 0, 1) and is parallel to the a-axis. By utilizing the Miller-Bravais indices, crystallographers can precisely define and communicate the orientation of specific planes within a hexagonal crystal [51].
- IV. The Miller-Bravais indices for hexagonal crystals are denoted as (hkl), where h, k and l are integers representing the intercepts of the plane with the crystallographic axes. These indices are determined by taking the reciprocals of the intercepts and reducing them to the smallest possible integers
- V. The significance of Miller-Bravais indices lies in their ability to provide a concise representation of crystallographic planes. By using these indices, crystallographers can easily communicate and analyze the orientation and intersection of planes within hexagonal crystals. This facilitates the understanding of crystal symmetry, crystal growth and the prediction of material properties [52].
- VI. Miller-Bravais indices allow for the determination of the spacing between adjacent planes in a crystal lattice. This spacing, known as the d-spacing, is related to the Miller-Bravais indices expressed in Eq. (24).

$$d = \frac{a}{\sqrt{h^2 + k^2 + hk}}, \quad (24)$$

where a is the lattice parameter, the d is a crucial parameter in X-ray diffraction studies, as it determines the angles at which constructive interference occurs, providing valuable information about the crystal structure [53]. The Miller-Bravais indices also enable the description of directions within a plane in hexagonal crystals. These directions are represented by three integers, (uvw) , where u , v and w are integers. The (uvw) indices correspond to a direction that is parallel to the vector (u, v, w) within a specific plane. These indices are determined by considering the relative positions of lattice points along the direction of interest.

14 | Lattice Planes in Relation to Miller Indices

In the field of Crystallography, lattice planes play a crucial role in understanding the arrangement of atoms within a crystal lattice. These planes are defined by their orientation and spacing and are commonly represented using Miller indices. Miller indices provide a concise and systematic way to describe the orientation of a lattice plane within a crystal structure [54]. The relationship between lattice planes and Miller indices are highlighted as follows:

- I. Lattice planes: a crystal lattice is a three-dimensional arrangement of atoms or molecules in a repeating pattern. Lattice planes are imaginary planes that pass through the crystal lattice and divide it into distinct regions. These planes are defined by their orientation with respect to the crystallographic axes. The orientation of a lattice plane is determined by its intercepts on the crystallographic axes, which are then used to calculate the Miller indices.
- II. Miller indices: Miller indices are a set of three integers enclosed in square brackets that represent the orientation of a lattice plane within a crystal structure. These indices are determined by taking the reciprocals of the intercepts made by the plane on the crystallographic axes and reducing them to the smallest possible integers. The resulting integers are then used as the Miller indices. The Miller indices of a lattice plane provide valuable information about its orientation and spacing within the crystal lattice. For example, a plane with Miller indices $[1\ 0\ 0]$ is parallel to the x -axis, while a plane with indices $[0\ 1\ 0]$ is parallel to the y -axis. The magnitude of the Miller indices also indicates the spacing between adjacent lattice planes. Higher indices correspond to planes that are closer together, while lower indices represent planes that are further apart [55].

15 | Importance in Crystallography

The use of Miller indices in Crystallography is of paramount importance and are stated as follows:

- I. They allow crystallographers to describe the orientation and spacing of lattice planes in a concise and standardized manner [56].
- II. They facilitate communication and understanding in the field of Crystallography.
- III. Miller indices provide a basis for the systematic study of crystal structures, enabling the prediction of crystallographic properties and behaviour.
- IV. The relationship between lattice planes and Miller indices is also crucial in the determination of crystal structures [57].
- V. Experimental techniques such as X-ray diffraction rely on the interaction of X-rays with lattice planes to produce diffraction patterns.
- VI. By analyzing these patterns, crystallographers can deduce the arrangement of atoms within a crystal lattice.
- VII. Miller indices are used to interpret the diffraction data and determine the crystal structure.

Lattice planes and Miller indices are fundamental concepts in Crystallography. Lattice planes divide the crystal lattice into distinct regions, while Miller indices provide a systematic way to describe their orientation and spacing [58]. Understanding the relationship between lattice planes and Miller indices is essential for the study and analysis of crystal structures. The use of Miller indices facilitates communication among researchers and enables the prediction and determination of crystallographic properties. Crystallography owes much of its progress to the development and application of Miller indices, making them an indispensable tool in the field.

16 | Diffraction in Crystals

Diffraction is a fundamental phenomenon in physics that occurs when waves encounter obstacles or pass through narrow openings. In the context of Crystallography, diffraction refers to the scattering of X-rays, electrons, or neutrons by a crystal lattice [59]. This process provides valuable information about the atomic arrangement within a crystal, allowing scientists to determine its structure and properties. Diffraction is primarily employed in the field of Crystallography to empirically ascertain the atomic and molecular arrangement of a crystal by exploiting the crystal's properties, which cause distinct crystalline structures to diffract the incoming X-ray beam into various Bragg reflection directions with varying intensities. Furthermore, both Bragg reflection geometry and Laue transmission geometry may be employed to concentrate a dispersed X-ray beam when the arrangement is circular in shape. The devices used for focusing are referred to as Bragg reflection lenses (Fig. 2A and Fig. 2B) and Laue transmission lenses (Fig. 2C and Fig. 2D). These lenses feature a circular configuration, resembling either a tube or a ring. A diagnostic imaging X-ray tube is utilized to produce a cone-shaped polychromatic X-ray beam that is directed towards the lens [60]. The majority of the beam's middle portion is absorbed by a shielding block, typically composed of lead. The X-ray photons on the fringe travel towards the outer ring or tube of the lens, which is composed of a very homogeneous single-crystal material. Following Bragg reflection or Laue transmission, the scattered photons are concentrated onto a specific point or small area along the central axis of the lens. This concentration leads to a significant increase in the intensity of X-ray photons at the focal point. The utilization of an X-ray focusing lens has the capacity to produce the most intense radiation dosage precisely at the focal point, making it highly promising for the application of radiosurgery in the treatment of cancer patients. For further information on the medical use of the X-ray Bragg reflection lens, the studies conducted by Moradi-Kurdestany et al. [61] can be referred to. Fig. 6a illustrates the diffraction process by a Bragg reflection geometry, Fig. 6b illustrates the design of a photon lens (tube, made of crystal) based on the Bragg reflection geometry, Fig. 6c illustrates the diffraction process by a special Laue transmission geometry while Fig. 6d illustrates the design of a photon lens (ring, made of crystal) based on the special design of a Laue transmission geometry.




Fig. 6. X-ray diffraction on a perfect crystal and the designs of two distinct lenses used to focus a scattered photon beam [60].

Crystals are solid materials with a highly ordered atomic structure, resulting in unique properties such as transparency, hardness and electrical conductivity. The study of crystals and their atomic arrangement has been of great interest to scientists for centuries [62]. One of the most powerful techniques used to investigate crystal structures is X-ray diffraction. This technique allows scientists to determine the arrangement of atoms within a crystal lattice by analyzing the diffraction patterns produced when X-rays interact with the crystal. Diffraction is a phenomenon that occurs when waves encounter an obstacle or pass through a narrow slit.

When X-rays, which are electromagnetic waves, interact with a crystal lattice, they diffract, or scatter, in a specific pattern [63]. This pattern is a result of constructive and destructive interference between the X-rays and the crystal lattice planes. The diffraction pattern can be captured on a detector and analyzed to determine the arrangement of atoms within the crystal.

17 | Principles of Diffraction in Crystals

Diffraction in crystals can be defined as the bending or spreading of waves as they encounter a periodic arrangement of atoms within a crystal lattice. When a beam of X-rays, electrons, or neutrons interacts with a crystal, it undergoes constructive and destructive interference due to the scattering of waves by the crystal's atoms [64]. This interference pattern is then recorded and analyzed to extract information about the crystal's structure. The diffraction of waves in crystals is governed by Bragg's law, which states that for constructive interference to occur, the path difference between two waves scattered by adjacent crystal planes must be an integer multiple of the wavelength of the incident wave [65]. This condition leads to the formation of a diffraction pattern, consisting of bright spots known as diffraction peaks, which correspond to the constructive interference of waves. The study of Crystallography has played a crucial role in understanding the arrangement of atoms within crystals [66]. One of the most powerful techniques used in Crystallography is X-ray diffraction, which allows scientists to determine the atomic arrangement by analyzing the diffraction lines produced when X-rays interact with a crystal. Diffraction occurs when waves encounter an obstacle or a slit, causing them to bend and spread out. In the case of X-ray diffraction, the obstacle is the crystal lattice and the X-rays are diffracted as they interact with the atoms within the crystal. The diffracted X-rays interfere constructively or destructively, resulting in a pattern of bright and dark spots known as diffraction lines or spots [67]. Diffraction lines are the key to deciphering the atomic arrangement within a crystal. By analyzing the positions, intensities and shapes of these lines, crystallographers can determine the crystal's unit cell dimensions, symmetry and atomic positions. This information is crucial for understanding the crystal's physical and chemical properties, as well as its potential applications in various fields.

18 | Impact of Diffraction in Crystallography

- I. Diffraction in crystals plays a crucial role in Crystallography, enabling scientists to determine the arrangement of atoms within a crystal [68].
- II. By analyzing the diffraction pattern, researchers can obtain information about the crystal's unit cell dimensions, symmetry and atomic positions.
- III. This knowledge is essential for understanding the crystal's physical and chemical properties, as well as for designing new materials with specific characteristics.
- IV. Diffraction techniques have revolutionized various scientific fields of X-ray diffraction, has been instrumental in elucidating the structures of complex molecules, such as proteins and DNA. This has paved the way for advancements in fields like biochemistry, pharmaceuticals and materials science [69].

Diffraction patterns obtained from X-ray Crystallography provide valuable information about the atomic arrangement within a crystal. By analyzing the diffraction pattern, scientists can determine the positions of atoms, the distances between them and the overall symmetry of the crystal lattice [70]. This information is crucial for understanding the physical and chemical properties of crystals, as well as for designing new materials with specific properties. Diffraction in crystals refers to the bending or spreading of waves as they encounter a periodic arrangement of atoms within a crystal lattice. This phenomenon is governed by Bragg's law, which describes the conditions for constructive interference between scattered waves. Diffraction in crystals is of paramount importance in Crystallography, allowing scientists to determine the atomic arrangement within a crystal and providing insights into its properties. The development of diffraction techniques, particularly X-ray diffraction, has revolutionized various scientific disciplines, leading to significant advancements in our understanding of complex molecules and materials.

19 | Applications of Crystallography

Crystallography has numerous applications in various scientific fields.

- I. In materials science, Crystallography helps in the development of new materials with desired properties, such as high strength or conductivity [71].
- II. In chemistry, Crystallography is used to determine the three-dimensional structures of molecules, which is essential for understanding their reactivity and designing new drugs.
- III. In biology, Crystallography plays a vital role in determining the structures of proteins and other biomolecules, aiding in the development of new drugs and understanding biological processes [72].

Crystallography has wide-ranging applications in materials science, chemistry and biology, contributing to advancements in various scientific fields. The study of diffraction patterns in crystals continues to be a fundamental tool for unraveling the mysteries of the atomic world.

20 | Diffraction Lines in Crystallography

- I. Diffraction lines provide valuable insights into the crystal's structure, allowing scientists to determine the positions of atoms within the crystal lattice. This knowledge is essential for understanding the crystal's properties, such as its mechanical, electrical and optical behaviour. For example, diffraction studies have been instrumental in understanding the structure of semiconductors, which are widely used in electronic devices [73].
- II. Diffraction lines enable the identification and characterization of unknown crystalline materials. By comparing the observed diffraction pattern with known crystal structures in databases, scientists can determine the crystal's composition and potentially discover new materials with unique properties. This has significant implications in materials science, where the development of novel materials is crucial for technological advancements [74].
- III. Diffraction lines also play a vital role in the field of protein Crystallography. Determining the three-dimensional structure of proteins is essential for understanding their functions and designing drugs that target specific proteins. X-ray diffraction is the primary technique used to obtain high-resolution protein structures and the analysis of diffraction lines allows scientists to reconstruct the electron density map of the protein, revealing its atomic details [75].

Diffraction lines are indispensable in Crystallography, providing valuable information about the atomic arrangement within crystals. By analyzing the diffraction pattern, crystallographers can determine the crystal's unit cell dimensions, symmetry and atomic positions, leading to a comprehensive understanding of its properties and potential applications. Diffraction lines have revolutionized various scientific fields, including materials science and protein Crystallography, enabling the discovery of new materials and the elucidation of protein structures [76], [77]. The study of diffraction lines continues to be a cornerstone in the quest to unravel the hidden structure of crystals and advance our knowledge of the natural world.

21 | Conclusion

This study has provided valuable insights into the principles of symmetry and diffraction lines in Crystallography. By understanding the arrangement of atoms within a crystal lattice, researchers are able to predict the diffraction patterns that will be produced when the crystal is subjected to X-ray or electron diffraction. The concept of symmetry within a lattice is crucial in determining the diffraction pattern that will be observed. The symmetry operations present within a crystal lattice, such as translations, rotations and reflections, dictate the positions of the diffraction lines in the resulting pattern. By analyzing the symmetry of a crystal lattice, researchers can predict the locations and intensities of diffraction lines, providing valuable information about the structure of the crystal. Furthermore, the study of diffraction lines in Crystallography has practical applications in various fields, including materials science, chemistry and biology. By analyzing

diffraction patterns, researchers can determine the atomic structure of a crystal, allowing for the development of new materials with specific properties or the elucidation of biological structures at the molecular level. The principles of crystal structures within Bravais lattices provide a solid foundation for understanding symmetry and diffraction lines in Crystallography. By studying the arrangement of atoms within a crystal lattice and analyzing the resulting diffraction patterns, researchers can gain valuable insights into the structure and properties of materials at the atomic level. This knowledge has wide-ranging implications for various scientific disciplines and has the potential to drive advancements in technology and innovation. Based on the findings obtained from this study, the following recommendations are suggested to further enlighten readers on the principles of crystal structures for Bravais lattice:

- I. It is essential to understand the concept of symmetry within a lattice. Symmetry operations such as rotation, reflection and translation play a crucial role in determining the overall symmetry of a crystal lattice. By analyzing the symmetry elements present in a crystal lattice, one can predict the possible crystal structures that can be formed. Therefore, it is recommended to study the symmetry operations in detail to accurately determine the crystal structure of a material.
- II. Diffraction lines in Crystallography provide valuable information about the arrangement of atoms in a crystal lattice. The diffraction pattern obtained from X-ray Crystallography can be used to determine the unit cell parameters and symmetry of a crystal lattice. By analyzing the diffraction lines, one can identify the Bravais lattice type and the space group of a crystal structure. Therefore, it is recommended to carefully analyze the diffraction lines to accurately determine the crystal structure of a material.

Hence, it is recommended that conventional studies and techniques in Crystallography be studied extensively to ensure the accuracy and reliability of the results obtained in the field. By adhering to these recommendations, researchers can advance their understanding of crystal structures and contribute to the field of Crystallography.

References

- [1] Mittemeijer, E. J., & Mittemeijer, E. J. (2011). Crystallography. In *Fundamentals of materials science: the microstructure-property relationship using metals as model systems* (pp. 103–200). Springer. https://link.springer.com/chapter/10.1007/978-3-642-10500-5_4
- [2] Dowsett, M., Wiesinger, R., & Adriaens, M. (2021). X-ray diffraction. In *Spectroscopy, diffraction and tomography in art and heritage science* (pp. 161–207). Elsevier. <https://doi.org/10.1016/B978-0-12-818860-6.00011-8>
- [3] Moore, E. A., & Smart, L. E. (2020). An introduction to crystal structures. In *Solid state chemistry: an introduction* (pp. 1–64). CRC Press. DOI: 10.1201/b12047-8
- [4] Pecharsky, V. K., & Zavalij, P. Y. (2009). Determination and refinement of the unit cell. In *Fundamentals of powder diffraction and structural characterization of materials* (pp. 407–495). Springer. https://link.springer.com/chapter/10.1007/978-0-387-09579-0_14
- [5] Ali, A., Chiang, Y. W., & Santos, R. M. (2022). X-ray diffraction techniques for mineral characterization: a review for engineers of the fundamentals, applications, and research directions. *Minerals*, 12(2), 205. DOI:10.3390/min12020205
- [6] Mckenzie, A. T., & Mckenzie, A. T. (1998). "Nature doth everywhere geometrize": crystals, crystallization, and Crystallography in the long eighteenth century 1. *Studies in eighteenth-century culture*, 27(1), 209–236. DOI:10.1353/sec.2010.0304
- [7] Scholz, E. (1989). Crystallographic symmetry concepts and group theory (1850-1880). In *Institutions and applications* (pp. 2–27). Elsevier. <https://doi.org/10.1016/B978-0-08-092546-2.50007-X>
- [8] Kikegawa, T., & Iwasaki, H. (1983). An X-ray diffraction study of lattice compression and phase transition of crystalline phosphorus. *Acta crystallographica section b: structural science*, 39(2), 158–164. <https://journals.iucr.org/paper?buy=yes&cnor=a22093&showscheme=yes&sing=yes>

- [9] Cheng, K. Y., & Cheng, K. Y. (2020). Atomic bonding and crystal structures. In *III–V compound semiconductors and devices: an introduction to fundamentals* (pp. 11–55). Springer. https://link.springer.com/chapter/10.1007/978-3-030-51903-2_2
- [10] Kubbinga, H. (2012). Crystallography from Haüy to Laue: controversies on the molecular and atomistic nature of solids. *Acta crystallographica section a: foundations of crystallography*, 68(1), 3–29.
- [11] Brückler, F. M., & Stilinović, V. (2023). From friezes to quasicrystals: a history of symmetry groups. In *Handbook of the history and philosophy of mathematical practice* (pp. 1–42). Springer. https://doi.org/10.1007/978-3-030-19071-2_132-2
- [12] Marcos, C. (2022). Periodicity, crystalline lattices, symbols, and notations. In *Crystallography: introduction to the study of minerals* (pp. 13–47). Springer. https://doi.org/10.1007/978-3-030-96783-3_2
- [13] Silva-Ramírez, E. L., Cumbreña-Conde, I., Cano-Crespo, R., & Cumbreña, F. L. (2023). Machine learning techniques for the ab initio Bravais lattice determination. *Expert systems*, 40(2), e13160. <https://doi.org/10.1111/exsy.13160>
- [14] Bunaciu, A. A., Udrişţoiu, E. G., & Aboul-Enein, H. Y. (2015). X-ray diffraction: instrumentation and applications. *Critical reviews in analytical chemistry*, 45(4), 289–299.
- [15] Lin, F., Liu, Y., Yu, X., Cheng, L., Singer, A., Shpyrko, O. G., ... & Doeff, M. M. (2017). Synchrotron X-ray analytical techniques for studying materials electrochemistry in rechargeable batteries. *Chemical reviews*, 117(21), 13123–13186. DOI:10.1021/acs.chemrev.7b00007
- [16] Giannini, C., Ladisa, M., Altamura, D., Siliqi, D., Sibillano, T., & De Caro, L. (2016). X-ray diffraction: a powerful technique for the multiple-length-scale structural analysis of nanomaterials. *Crystals*, 6(8), 87. DOI:10.3390/cryst6080087
- [17] Bhardwaj, J., Sastri, O., & Sharda, V. (2017). Stacking 2-D lattices to construct 3-D Bravais lattices. *Physics education*, 1–10. https://www.researchgate.net/profile/Oruganti-Sastri/publication/323966454_Stacking_2-D_Lattices_to_Construct_3-D_Bravais_Lattices/links/5ab5123445851515f5996d41/Stacking-2-D-Lattices-to-Construct-3-D-Bravais-Lattices.pdf
- [18] Hoffmann, F., & Hoffmann, F. (2020). Crystal shapes and Bravais lattices. In *Introduction to crystallography* (pp. 33–89). Springer. https://link.springer.com/chapter/10.1007/978-3-030-35110-6_2
- [19] Grimmer, H. (2015). Partial order among the 14 Bravais types of lattices: Basics and applications. *Acta crystallographica section a: foundations and advances*, 71(2), 143–149. DOI:10.1107/S2053273314027351
- [20] Su, C. Y., Cai, Y. P., Chen, C. L., Smith, M. D., Kaim, W., & Zur Loye, H. C. (2003). Ligand-directed molecular architectures: self-assembly of two-dimensional rectangular metallacycles and three-dimensional trigonal or tetragonal prisms. *Journal of the american chemical society*, 125(28), 8595–8613. DOI:10.1021/ja034267k
- [21] Borisov, S. V., Magarill, S. A., & Pervukhina, N. V. (2012). An interpretation of three intersections of cubic and rhombohedral structures based on the conservative nature of force skeletons. *Crystallography reports*, 57(5), 656–660. DOI:10.1134/S1063774512050033
- [22] Evarestov, R. A. (2007). Space groups and crystalline structures. In *Quantum chemistry of solids: the lcao first principles treatment of crystals* (pp. 7–46). Springer. https://link.springer.com/chapter/10.1007/978-3-540-48748-7_2
- [23] Mehla, S. (2022). Design and fabrication of gold microelectrode arrays for sers-based chemical sensing. DOI: 10.13140/RG.2.2.13913.60003
- [24] Spruiell, J. E., & Clark, E. S. (1980). Unit cell and crystallinity. In *Methods in experimental physics* (Vol. 16, pp. 1–127). Elsevier. DOI: 10.1016/S0076-695X(08)60756-5
- [25] Grimvall, G., Magyari-Köpe, B., Ozoliņš, V., & Persson, K. A. (2012). Lattice instabilities in metallic elements. *Reviews of modern physics*, 84(2), 945–986. DOI:10.1103/RevModPhys.84.945
- [26] Sólyom, J., & Sólyom, J. (2007). The structure of crystals. In *Fundamentals of the physics of solids: volume I structure and dynamics* (pp. 203–240). Springer. https://link.springer.com/chapter/10.1007/978-3-540-72600-5_7
- [27] Moeck, P., & DeStefano, P. (2018). Accurate lattice parameters from 2D-periodic images for subsequent Bravais lattice type assignments. *Advanced structural and chemical imaging*, 4(1), 1–33. DOI:10.1186/s40679-018-0051-z

- [28] Chatterjee, S. K. (2008). Crystal symmetry (crystal pattern): I. In *Crystallography and the world of symmetry* (pp. 23–33). Springer. https://link.springer.com/chapter/10.1007/978-3-540-69899-9_4
- [29] Massa, W., & Massa, W. (2004). Crystal lattices. In *Crystal structure determination* (pp. 3–11). Springer. https://link.springer.com/chapter/10.1007/978-3-662-06431-3_2
- [30] Venderbos, J. W. F. (2016). Symmetry analysis of translational symmetry broken density waves: application to hexagonal lattices in two dimensions. *Physical review B*, 93(11), 115107. DOI:10.1103/PhysRevB.93.115107
- [31] Perez, N. (2024). Atomic structure. In *Materials science: theory and engineering* (pp. 1–50). Springer. https://link.springer.com/chapter/10.1007/978-3-031-57152-7_1
- [32] Malgrange, C., Ricolleau, C., & Schlenker, M. (2014). *Symmetry and physical properties of crystals*. Springer.
- [33] Liu, Y., Liu, Y., & Drew, M. G. B. (2017). Comparison of calculations for interplanar distances in a crystal lattice. *Crystallography reviews*, 23(4), 252–301. DOI:10.1080/0889311X.2017.1323332
- [34] Klingshirn, C. F., & Klingshirn, C. F. (2012). Crystals, lattices, lattice vibrations and phonons. In *Semiconductor optics* (pp. 135–166). Springer. https://link.springer.com/chapter/10.1007/978-3-642-28362-8_7
- [35] Muller, P. (2009). Practical suggestions for better crystal structures. *Crystallography reviews*, 15(1), 57–83. DOI:10.1080/08893110802547240
- [36] Zhang, W. Z., & Weatherly, G. C. (2005). On the crystallography of precipitation. *Progress in materials science*, 50(2), 181–292.
- [37] Djohari, H., Milstein, F., & Maroudas, D. (2007). Stability of simple cubic crystals. *Applied physics letters*, 90(16). DOI:10.1063/1.2724918
- [38] Keen, D. A., & Goodwin, A. L. (2015). The crystallography of correlated disorder. *Nature*, 521(7552), 303–309. DOI:10.1038/nature14453
- [39] Gault, B., Moody, M. P., Cairney, J. M., & Ringer, S. P. (2012). Atom probe crystallography. *Materials today*, 15(9), 378–386. DOI:10.1016/S1369-7021(12)70164-5
- [40] Sun, S., Zhang, X., Cui, J., & Liang, S. (2020). Identification of the Miller indices of a crystallographic plane: a tutorial and a comprehensive review on fundamental theory, universal methods based on different case studies and matters needing attention. *Nanoscale*, 12(32), 16657–16677. DOI:10.1039/d0nr03637d
- [41] Banadaki, A. D., & Patala, S. (2015). An efficient algorithm for computing the primitive bases of a general lattice plane. *Journal of applied crystallography*, 48(2), 585–588.
- [42] He, Y. (2024). Stereographic projection of theoretical orientation relationships between crystals of any types in phase transformation and precipitation. *Crystal research and technology*, 59(1), 2300242. <https://doi.org/10.1002/crat.202300242>
- [43] Hermann, K. (2009). Basics of crystallography. In *Computational methods in catalysis and materials science: an introduction for scientists and engineers* (pp. 265–294). Wiley Online Library. DOI: 10.1002/9783527625482
- [44] Prince, E., & Paufler, P. (1995). Mathematical techniques in crystallography and materials science. *Crystal research and technology*, 30(3), 318.
- [45] Hauptman, H. A. (1991). The phase problem of x-ray crystallography. *Reports on progress in physics*, 54(11), 1427. DOI: 10.1088/0034-4885/54/11/002
- [46] Ameh, E. S. (2019). A review of basic crystallography and x-ray diffraction applications. *International journal of advanced manufacturing technology*, 105(7–8), 3289–3302. DOI:10.1007/s00170-019-04508-1
- [47] Michalski, E. P. (2018). On the new characteristics of Miller indices for centered lattices. *Bulletin of the polish academy of sciences, technical sciences*, 66(4), 529–538. DOI:10.24425/124269
- [48] Zhang, M. X., & Kelly, P. M. (2009). Crystallographic features of phase transformations in solids. *Progress in materials science*, 54(8), 1101–1170. <https://doi.org/10.1016/j.pmatsci.2009.06.001>
- [49] Im, S. W., Ahn, H. Y., Kim, R. M., Cho, N. H., Kim, H., Lim, Y. C., ... & Nam, K. T. (2020). Chiral surface and geometry of metal nanocrystals. *Advanced materials*, 32(41), 1905758. DOI:10.1002/adma.201905758
- [50] Petříček, V., Dušek, M., & Plášil, J. (2016). Crystallographic computing system Jana2006: solution and refinement of twinned structures. *Zeitschrift fur kristallographie-crystalline materials*, 231(10), 583–599. DOI:10.1515/zkri-2016-1956

- [51] Janner, A., & Janssen, T. (2015). From crystal morphology to molecular and scale crystallography. *Physica scripta*, 90(8), 88007. DOI:10.1088/0031-8949/90/8/088007
- [52] Suwas, S., & Ray, R. K. (2014). *Crystallographic texture of materials*. Springer. <https://doi.org/10.1007/978-1-4471-6314-5>
- [53] Gottstein, G., & Gottstein, G. (2004). Atomic structure of solids. In *Physical foundations of materials science* (pp. 13–62). Springer. https://link.springer.com/chapter/10.1007/978-3-662-09291-0_3
- [54] Wahab, M. A. (2024). *Mirror symmetry: the mother of all crystal symmetries*. Springer. <https://link.springer.com/book/10.1007/978-981-99-8361-2>
- [55] Nespolo, M. (2018). Geometry of crystals, polycrystals, and phase transformations. By Harshad KDH Bhadeshia. CRC Press, 2018. Hardcover, Pp. xv+ 251. Price GBP 37.59. ISBN 9781138070783. *Foundations of crystallography*, 74(2), 153–155.
- [56] Nespolo, M. (2015). The ash heap of crystallography: restoring forgotten basic knowledge. *Journal of applied crystallography*, 48(4), 1290–1298. DOI:10.1107/S1600576715011206
- [57] Galiulin, R. V. (1981). Crystallographic geometry. *Acta crystallographica section a foundations of crystallography*, 37(a1), C350–C350. DOI:10.1107/s0108767381089162
- [58] Okamoto, P. R., & Thomas, G. (1968). On the four-axis hexagonal reciprocal lattice and its use in the indexing of transmission electron diffraction patterns. *Physica status solidi (B)*, 25(1), 81–91. DOI:10.1002/pssb.19680250106
- [59] Fetisov, G. V. (2020). X-ray diffraction methods for structural diagnostics of materials: progress and achievements. *Physics-uspekhi*, 63(1), 2. DOI: 10.3367/UFNe.2018.10.038435
- [60] Guan, F., Asai, M., Bartkoski, D. A., Kleckner, M., Harel, Z., & Salehpour, M. (2023). Adding the X-ray Bragg reflection physical process in crystal to the Geant4 Monte Carlo simulation toolkit, part I: reflection from a crystal slab. *Precision radiation oncology*, 7(1), 59–66. DOI:10.1002/pro6.1188
- [61] Moradi-Kurdestany, J., Bartkoski, D. A., Tailor, R., Mirkovic, D., Harel, Z., Bar-David, A., ... & Salehpour, M. (2022). Dosimetry of a novel focused monoenergetic beam for radiotherapy. *Physics in medicine and biology*, 67(7), 07NT01. DOI:10.1088/1361-6560/ac5c8f
- [62] Shahbazi, H., Tataei, M., Enayati, M. H., Shafeiey, A., & Malekabadi, M. A. (2019). Structure-transmittance relationship in transparent ceramics. *Journal of alloys and compounds*, 785, 260–285. DOI:10.1016/j.jallcom.2019.01.124
- [63] Bettini, A., & Bettini, A. (2017). Diffraction, interference, coherence. In *A course in classical physics 4-waves and light* (pp. 175–233). Springer. https://link.springer.com/chapter/10.1007/978-3-319-48329-0_5
- [64] Mingos, D. M. P. (2020). Early history of x-ray crystallography. In *21st century challenges in chemical crystallography I: history and technical developments* (pp. 1–41). Springer. https://link.springer.com/chapter/10.1007/430_2020_73
- [65] Schwartz, L. H., Cohen, J. B., Schwartz, L. H., & Cohen, J. B. (1987). The nature of diffraction. In *Diffraction from materials* (pp. 46–76). Springer. https://link.springer.com/chapter/10.1007/978-3-642-82927-7_2
- [66] Vainshtein, B. K. (2013). *Fundamentals of crystals: symmetry, and methods of structural crystallography* (Vol. 1). Springer Science & Business Media. https://books.google.com/books/about/Fundamentals_of_Crystals.html?id=AtPqCAAQBAJ
- [67] Esterhuysen, C. (2014). Crystallography-a modern science with a rich history. *Quest*, 10(3), 3–8.
- [68] De Graef, M., & McHenry, M. E. (2012). *Structure of materials: an introduction to crystallography, diffraction and symmetry*. Cambridge University Press.
- [69] Macchi, P. (2020). The connubium between crystallography and quantum mechanics. *Crystallography reviews*, 26(4), 209–268.
- [70] Waseda, Y., Matsubara, E., & Shinoda, K. (2011). *X-ray diffraction crystallography; introduction, examples and solved problems*. Zhurnal Eksperimental'noi i Teoreticheskoi Fiziki. Springer Science & Business Media. <http://scholar.google.com/scholar?hl=en&btnG=Search&q=intitle:No+Title#0>
- [71] Zheng, H., Hou, J., Zimmerman, M. D., Wlodawer, A., & Minor, W. (2014). The future of crystallography in drug discovery. *Expert opinion on drug discovery*, 9(2), 125–137. DOI:10.1517/17460441.2014.872623
- [72] Bruno, I., Gražulis, S., Helliwell, J. R., Kabekkodu, S. N., McMahon, B., & Westbrook, J. (2017). Crystallography and databases. *Data science journal*, 16, 38. DOI:10.5334/dsj-2017-038

- [73] Ziletti, A., Kumar, D., Scheffler, M., & Ghiringhelli, L. M. (2018). Insightful classification of crystal structures using deep learning. *Nature communications*, 9(1), 2775. DOI:10.1038/s41467-018-05169-6
- [74] Rathore, I., Mishra, V., & Bhaumik, P. (2021). Advancements in macromolecular crystallography: from past to present. *Emerging topics in life sciences*, 5(1), 127–149. DOI:10.1042/ETLS20200316
- [75] Hoja, J., Reilly, A. M., & Tkatchenko, A. (2017). First-principles modeling of molecular crystals: structures and stabilities, temperature and pressure. *Wiley interdisciplinary reviews: computational molecular science*, 7(1), e1294. DOI:10.1002/wcms.1294
- [76] Su, X. D., Zhang, H., Terwilliger, T. C., Liljas, A., Xiao, J., & Dong, Y. (2015). Protein crystallography from the perspective of technology developments. *Crystallography reviews*, 21(1–2), 122–153. DOI:10.1080/0889311X.2014.973868
- [77] Dauter, Z., & Wlodawer, A. (2016). Progress in protein crystallography. *Protein & peptide letters*, 23(3), 201–210. DOI:10.2174/0929866523666160106153524